

EPDM/SBR Rubber E8350

Specifications	Values
Colour	Black
Hardness, °Shore A	50 ± 5
Density, g/cm ³	1.35
Elongation at Break, %	300
Tensile Strength, Mpa	5
Temperature Range in Air	-30 to +100° C

Rev. 01

.The function and durability of gaskets are highly dependant on the application and the medium. Since the conditions of use are beyond our control, ELWIS ROYAL can only be held responsible for the characteristics of the material and for the geometrical shape of the gasket.