

# Viroid

## Description:

Viroid is a plasticised gelatine impregnated cellulose based material.

<b>Parameters</b>	<b>Values</b>
Density	0,72 g/cm <sup>3</sup>
Maximum Recommended Service Temperature	120° C
Tensile Strength	14 N/mm <sup>2</sup>
Compressibility ASTM F36/G	25-40 %
Recovery      ASTM F36/G	min. 40 %
<b>ASTM fuel B - 22 Hours at 21-30° C:</b>	
Weight Increase	max. 15 %
Thickness Increase	max. 5 %
<b>ASTM oil no. 3 - 22 Hours at 21-30° C:</b>	
Weight Increase	max. 15 %
Thickness Increase	max. 5 %

## Applications:

An economical gasket material for general flange joints, i.e. water pumps and gearboxes. Excellent oil, fuel, and anti freeze resistance.